

Dousselin

BP 23 - 2 Rue GPERI 69270 COUZON au MONT D'OR
Tel 04 72 42 96 00 Fax 04 72 42 96 09
Site: www.dousselin.fr mail: dousselin@wanadoo.fr

PONCES GRADES H

COMPOSITION CHIMIQUE		
SiO ₂		70.5
Al ₃ O ₃		13.5
Na ₂ O		1.6
K ₂ O		1.8
Fe ₂ O ₃		1.1
CaO+MgO		1.3
MgO		0.5
TiO ₂		0.2

INFORMATION TECHNIQUES		
MASSE VOLUMIQUE REELLE		2.35
HUMIDITE		< 0.1%
DURETE MOHS		6
pH		7 - 8

H	
REF	TAILLE
1/0N	0 - 250 µ
2/0N	0 - 250 µ
3/0N	0 - 150 µ
FF	0 - 105 µ
70 LHM	0 - 210 µ
G1/2	106 - 300 µ
2	250 - 600 µ
4	250 - 1400 µ
NCS-12	0 - 60 µ
FFFF	0 - 75 µ
4/0N	0 - 125 µ
F	0 - 150 µ
1/2B	106 - 300 µ
2B	180 - 425 µ
4	300 - 1400 µ
8/12 BF	1400 - 3350 µ
8/12	1400 - 3350 µ
13 LHM	2000 - 4750 µ

Références sur stock